



COLORIFICIO VENEZIANO

the Art  
of  
Paint

## GRASSELLO 600

Lime Line

### Characteristics

Technical data Specific weight: 1,550 Kg/l  $\pm$  0,05 Granulometry: 200  $\mu$  max  
Appereance: Paste Consumption: about 1 kg/m<sup>2</sup> when finished Apply on any surface  
paying attention to thin mortars. Check if it is well attached to the base.

Water vapor Diffusion: 370 g/m<sup>2</sup> in 24 hours Resistance Factor to vapor diffusion:  
 $\mu=10$  Air equivalent layer:  $S_d = \mu \cdot s = 0.06$  m (calculated with  $s = 0.6 \cdot 10^{-3}$ m)  
Coefficient of water absorbtion:  $w = 0.2$  kg (m<sup>2</sup>  $\cdot$  h<sup>1/2</sup>).  $\mu S_d \cdot w = 0.012$  kg (m  $\cdot$  h<sup>1/2</sup>).  
Respects the theory by Kuenzle.

### Other

Base Preparation and application cycles Remove any dust and dirt spot from the  
plasterboard surfaces or walls that have been already painted. Check the plasters or  
the old paintings consistency. If it is a tempera painting then insulate with Isoedil-A.  
For plasterboards apply one layer of Fondo Ruvido. Apply then the first layer of  
GRASSELLO 600 with a steel trowel. After about 12 hours (according to the  
temperature) apply the second layer. After 1 hour apply the finishing in order to have  
the desired effect (the more you smooth GRASSELLO 600, the more it gest shiny). If  
the base requires thicker depths we suggest to use Marmorino Polvere Media or  
Marmorino Pasta Media. For the protection of GRASSELLO 600, wait until it is dry, then  
apply Idrocem-A or a powder wax or a paste wax.

Warnings Avoid the application if temperature is lower than +5 °C and with relative  
humidity higher than 75%. Avoid the application in the coldest months. Facades  
coated with GRASSELLO 600, during the lay up and the days after the drying up must  
be protected from rain otherwise white spots may show up.

Supply Can: 25 kg. Tints: see colors folder.

Preservation GRASSELLO 600 is constantly and properly checked. The raw materials used are strictly selected and checked.

---

THE REPORTED DATA REFER TO LABORATORY TESTS: DURING PRACTICAL APPLICATIONS IN BUILDING SITES THESE CAN BE SLIGHTLY MODIFIED ACCORDING TO THE CONDITIONS OF ANY INSTALLATION. THE PERSON WHO WORKS WITH THE PRODUCT MUST VERIFY THE EXPECTED SUITABILITY OF USE OF THE PRODUCT, TAKING UPON HIMSELF.

THE COMPANY COLORIFICIO VENEZIANO S.R.L. MAY CARRY OUT TECHNICAL ALTERATIONS ON PRODUCTS WITHOUT NOTICE.