



COLORIFICIO VENEZIANO

the Art of Paint

SILOXAN INTO

Professional Line

Characteristics

Features Specific weight: 1.750 kg/l Dilution: ready to use Available in the following granulometry: 0.6, 1.2, 1.5, 2.0

Consumption Granulometry 0.6 mm: 2.5 kg/m² with two hands Granulometry 1.0 mm: 2.0 kg/m² Granulometry 1.2 mm: 2.3 kg/m² Granulometry 1.5 mm: 1.5 kg/m² Granulometry 2.0 mm: 3.0 kg/m² with two hands It allows to obtain a finishing surface with a rustic effect.

Technical Data Certificato CE

EN 15824

SPEED TRANSMISSION OF STEAM EN ISO 7783-2 Category Spread equivalent to the thickness of the air layer Sd/m V2 Medium Value between $\geq 0,14$ <1,4 WATER ABSORPTION EN 1062-3 Category Spread equivalent to the thickness of the air layer Sd/m W3 Low $\geq$ Value between $\geq 0,14$ <1,4> GRIP EN 1542 (test carried out in a time of 28 days mandatory technical) All measured values must be at least 0.3 MPa (mean value recorded 1.58 Mpa) DURABILITY EN 13687-3 All measured values must be at least 0.3 MPa (mean value recorded 2.34 Mpa) n.b. prove effettuate da: N.B. Tests done by: Laboratory aut. by the Ministry of Infrastructure and Transport P.C.S. LL.PP.S.T.C. -law November 5 1971 n. 1086 Dec. N $\geq$ 56300 of 14/03/2007 Laboratory aut. by the Ministry of Infrastructure and Transport P.C.S. LL.PP.S.T.C. $\geq$ Presidential Decree No. 380/01 art. 59 circ. n $\geq$ 349/99 weeks. a), b) and c) Dec. n $\geq$ 53362 of 06/05/2005 Notified Body n $\geq$ 1308 (DM 826 149 of 22/03/2004 of the Ministry of Industry) under Dir. 89/106 / EEC, DPR No. 246/1993, DM 156/2003

Other

Use SILOXAN INTO is used as protective and decorative coating for indoor and outdoor use, on bottom plasters with a lime-cement base, especially where having at the same time high transpirability and low water absorption is necessary.

Base preparation The finishing coating must be applied after at least 28 days from the bottom plaster application. The surface needs to be dry and clean, without any other greasy spots and must be completely clean.

Application Lay the material on the surface with a metallic spatula taking care of distributing one uniform layer of material. The finishing must be completed with a plastic spatula making circular movements. To apply the product with a fine 0.6 mm granulometry, you need 2 layers of material. The second layer must be applied when the first one is completely dry.

Warnings For every work just take the needed material all of the same kind. Apply the material only over seasoned and dried plasters. Avoid the application on facades with full sun and too much wind. Avoid the application during the coldest and most humid months of the year; a temperature of +5 °C is the lowest value for the laying-up and drying of the material. After applying, the surfaces must be protected by rain for at least 48 hours. Avoid the application of the material over a facade in different times. SILOXAN INTO must be used at its original status without adding other materials.

Supply 25 kg can. Tints: see the colors folder.

Preservation Preserve the product in right places. If stocked inside the original can it lasts 1year.

Quality SILOXAN INTO is constantly and properly checked in our laboratories. The raw materials used are strictly selected and checked.

THE REPORTED DATA REFER TO LABORATORY TESTS: DURING PRACTICAL APPLICATIONS IN BUILDING SITES THESE CAN BE SLIGHTLY MODIFIED ACCORDING TO THE CONDITIONS OF ANY INSTALLATION. THE PERSON WHO WORKS WITH THE PRODUCT MUST VERIFY THE EXPECTED SUITABILITY OF USE OF THE PRODUCT, TAKING UPON HIMSELF.

THE COMPANY COLORIFICIO VENEZIANO S.R.L. MAY CARRY OUT TECHNICAL ALTERATIONS ON PRODUCTS WITHOUT NOTICE.